

FILTER CREPE PAPER FOR FAP COFFE CAPSULES

	UoM	FIB055
Version		Standard
BASE PAPER WEIGHT	gsm	÷ 50
CREPE PAPER WEIGHT	gsm	54 ± 3
THICKNESS (CREPE)	mm.	0,19 ± 0,03
THICKNESS (STRETCHED)	mm.	0,13
DENSITY	gr/cm ³	0,290
TENSILE STRENGTH (MD)	N/15mm	> 16 N
TENSILE STRENGTH (CD)	N/15mm	> 12N
ELONGATION (MD)	%	> 8 %
ACQUESOUS EXTRACT	Ph	06-08
WATER POROSITY	CC/60"	320 - 420
WET STRENGTH (MD)	N/15mm	> 5
WET STRENGTH (CD)	N/15mm	> 3