

WHITE FILTER CREPE PAPERS FOR C.A.V. FILTER CARTRIDGES

	UoM	FCB083	FCB091	FCB093
CREPE PAPER WEIGHT	gsm	90 ± 4	90 ± 4	90 ± 2
THICKNESS (CREPE)	mm.	> 0,30	> 0,35	> 0,33
TENSILE STRENGTH (MD-DRY)	N/15mm	> 33N	> 35N	> 33N
TENSILE STRENGTH (MD-WET)	N/15mm	> 5N	> 6N	> N7
ELONGATION (MD)	%	> 10%	> 10%	> 10%
WATER POROSITY *	c ³ /60"	80 - 120	40 - 60	80 - 120
AIR POROSITY*	c ³ /60"	400 -600	> 600	> 500
BURSTING TRENGTH	kPa	> 2	> 2	> 2
BUBBLE TEST	mm/H ² O	> 220	> 190	> 200
OPTIMAL PORE SIZE	micron	> 8	> 10,4	> 9,5
MAX PORE DIAM	micron	> 39,7	> 46	> 43,7

* INTERNAL METHOD