

## CREPE PAPER FOR BOOKBINDING

	UoM	LEB070	LEB090	LB2090	LB1110	LB1114	LEA090
Version		<b>White</b>	<b>White</b>	<b>White</b>	<b>White</b>	<b>White</b>	<b>Brown</b>
BASE PAPER WEIGHT	gsm	÷ 70	÷ 80	÷ 70	÷ 85	÷ 85	÷ 85
CREPE PAPER WEIGHT	gsm	75 ± 5	85 ± 5	90 ± 5	110 ± 5	110 ± 5	90 ± 5
THICKNESS (crepe)	mm.	0,22 ± 0,03	0,21 ± 0,03	0,30 ± 0,2	0,41± 0,03	0,41± 0,03	N.A.
DENSITY	gr/cm <sup>3</sup>	0,340	0,400	0,300	0,270	0,270	N.A.
TENSILE STRENGTH (MD)	N/15mm	> 30N	> 24N	> 19N	> 30N	> 30N	> 23N
ELONGATION (MD)	%	> 17 %	> 7%	> 30 %	> 35%	> 50%	> 6 %
COBB VALUE (300")	gr/sqm	60-80	< 90	80-120	< 90	100-130	< 50