

CREPE PAPER GRADES FOR GRINDING WHEELS

Version	UoM	NER041	NER051
CREPE PAPER WEIGHT	gsm	40 ± 2	50 ± 2
THICKNESS (CREPE)	mm.	0,08 ± 0,02	0,10 ± 0,02
TENSILE STRENGTH (MD)	N/15mm	> 6 N	> 6 N
ELONGATION (MD)	%	> 14 %	> 14 %
AIR POROSITY	c ³ /60"	60 - 90	< 100
GURLEY		> 10	> 10